

Kapci 616 Addflex

1-Characteristic properties:

An additive specially formulated for mixing with two component polyurethane paints to improve its flexibility.

2-Materials for application:

Addflex Kapci 616

3-Mixing ratio (by volume):

30 % of addflex 616 as supplied should be added to the paint or clear coat before thinning. Hardener and thinner then can be added to the mixture in the normal amounts recommended for paint or clear coat.

4-Spraying process:

Addflex Kapci 616 can be mixed with Kapcicryl (Kapci 660), Kapciclear (C888) and any other two component paints to make it flexible enough for application on plastic car parts.

5-Packaging:

0.5 and 1 Liter

6-Color:

Transparent.

7-Shelf life:

24 months at 20°C

8-Material safety data

When using these products it is required to comply with the national regulations for health and safety.

9-Flash points and transport classification

Product	Flash point	ADR transport code
Filler hardener Kapci 621	21-55°C	3-31C

The data on the label of the products must be considered.

Storage and transportation should comply with the local laws

The information given in this data sheet is based upon our best knowledge and experience with the application conditions set to Kapci standards. The customers are requested to verify the results by their own selves to make sure that the product is suitable for their applications and application conditions.

This document is computer generated therefore it is not signed.

Issued on 30/10/2000

Page 1 of 1

Printed 28/04/2001

This document was created with Win2PDF available at <http://www.daneprairie.com>.
The unregistered version of Win2PDF is for evaluation or non-commercial use only.